



P8

Inspection Document
EN 10204
Prüfbescheinigung

HILTI (CHINA) LTD.
Yongping Road, South,
Zhanjiang, Guangdong, PRC

Document No. *Dokument Nr.*

P8_2.2_028

Item-Nr.	Product designation	Customer ref. -Nr.	Batch-Nr.	Quantity
Sach-Nr.	Produktbezeichnung	Kunden Ref. Nr.	Charge/Los Nr.	Menge
Code art.	Référence produit	No. ref. de client	Commande No.	Quantité
259945	HAS-R M8x80/14			

Item designation	HAS-R	Rod M8	Nut M8	Washer 8.4		
Sachbezeichnung	M8x80/14					
Reference composant						

Inspection values/Prüfergebnisse

Chemical composition		set value	actual value	set value	actual value	set value	actual value	set value	actual value	set value	actual value
Chem. Zusammensetzung											
C %		0.00-0.07	0.02	0.00-0.08	0.01	0.00-0.08	0.01				
Si %		0.00-1.00	0.35	0.00-1.00	0.51	0.00-1.00	0.39				
Mn %		0.00-2.00	1.81	0.00-2.00	1.51	0.00-2.00	1.44				
P %		0.000-0.045	0.031	0.000-0.050	0.030	0.000-0.050	0.029				
S %		0.000-0.030	0.025	0.000-0.030	0.001	0.000-0.030	0.002				
Cr %		16.50-18.50	16.76	16.00-18.50	17.33	16.00-18.50	17.14				
Mo %		2.00-2.50	2.01	2.00-3.00	2.08	2.00-3.00	2.03				
Ni %		10.00-13.00	10.12	10.00-14.00	10.07	10.00-14.00	10.11				
Cu %											
B %											
Al %											
N %		0.00-0.11	0.075								
Pb %											
Mech. properties											
Mechanische Eigensch. / Mecan. prop.											
N											
V											
Fp				26	26						
HV						140-250	143				
A		min.10	23								
Z											
R _{p0.2}		min.350	630								
R _m		700-850	830								
Layer thickness/Schichtdicke											
Epaisseur de couche extérieure											
d (Zn)											
N	kN	Tension load / Bruchlast Zug / charge de tension				Z	%	Reduction of area / Einschnürung / contraction			
V	kN	Shear load / Querlast / charge de cisaillement				R _{p0.2}	N/mm ²	Yield strength / Streckgrenze / limite d'elasticite			
F _p	N	Proof load / Prüfkraft / charge limite				R _m	N/mm ²	Ultimate tensile strength / Zugfestigkeit / resistance a la			
HV	-	Vickers hardness / Härte Vickers / durete Vickers				d (Zn)	µm	Mean zinc thickness/ mittlere Schicht-dicke Zn / epaisseur			
A	%	Elongation after fracture / Bruch-dehnung / elongation apres fracture									